

(19)



JAPANESE PATENT OFFICE

PATENT ABSTRACTS OF JAPAN

(11) Publication number: **2000348537 A**

(43) Date of publication of application: **15.12.00**

(51) Int. Cl. **H01B 1/24**
H01B 13/00
H01M 4/62
// B01F 7/16
C09C 1/48
C09D 5/24

(21) Application number: **11244229**
(22) Date of filing: **31.08.99**
(30) Priority: **31.03.99 JP 11091088**

(71) Applicant: **LION CORP**
(72) Inventor: **KANAMARU MINAKO**
TATSUMI KOICHI
SHIRAIISHI AKIO

(54) **CONDUCTIVE PASTE, MANUFACTURE
THEREOF, AND CONDUCTIVE AUXILIARY
AGENT FOR SECONDARY BATTERY**

(57) Abstract:

PROBLEM TO BE SOLVED: To provide a conductive paste containing carbon black having a high electro-conductivity of improved stability for storing (stability in coagulation and sedimentation).

SOLUTION: A conductive paste contains carbon

black and a dispersing medium wherein the carbon black has such characteristics as a specific surface area of 700-1,500 m²/g, a primary particle size of 10-40 nm, and a DBP oil absorption amount of 300-600 mL/100 g, and the paste has a viscosity of 1,000-100,000 mPa.s. The dispersing medium is water, and 0.5-25 pts.wt. carbon black and 0.01-15 pts.wt. dispersing agent are included with respect to 100 pts.wt. of paste.

COPYRIGHT: (C)2000,JPO